


REMARKS

The present amendment seeks to place the application in better conformance with U.S. practice. A page containing an abstract of the disclosure is enclosed.

Entry of the amendment is requested.

Respectfully submitted,

By



Aron Preis
Attorney for Applicants
Reg. No. 29,426

Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741
(412) 777-8343
FACSIMILE PHONE NUMBER:
(412) 777-8363
s:\ap\kgb2411pa

Version with markings to show changes

IN THE CLAIMS:

Please amend as follows:

1. [Thermoplastic moulding compositions] A thermoplastic molding composition comprising thermoplastic polycarbonate and 0.01 to 30 parts by wt. of an aluminum compound, said part by wt. being per 100 parts by wt. of polycarbonate [aluminium compounds] said compound having an average particle diameter of 1 nm - 20 μ m.
2. [Thermoplastic moulding compositions] The composition according to claim 1, characterized in that the average particle diameter of the [aluminium] compound is 1 nm - 10 μ m.
3. [Thermoplastic moulding compositions] The composition according to claim 1, characterized in that [that] said average particle diameter of the [aluminium] compound is 5 - 500 nm.
4. [Thermoplastic moulding] The composition according to claim 1, [characterized in that it comprises] wherein said compound is a member selected from the group consisting of oxides, water-containing oxides, phosphates, sulfates, sulfides, sulfites, hydroxides, borates [or] and borophosphates of aluminium.
5. [Thermoplastic moulding] The composition according to claim 1 comprising
 - A. 40 to 99 parts by wt. aromatic polycarbonate,
 - B. 0 to 50 parts by wt. vinyl copolymer,
 - C. 0.5 to 60 parts by wt. graft polymer,

- D. 0.1 to 30 parts by wt. aluminium compound.
6. [Moulding compositions] The composition according to claim 1, comprising 50 to 95 parts by wt. aromatic polycarbonate [A] .
7. [Moulding compositions] The composition according to claim 5, [comprising] wherein graft [polymers] polymer C [prepared by] is a product of copolymerization of
- 5 to 95 parts by wt. of a mixture of
- 50 to 95 parts by wt. styrene, α -methylstyrene, styrene substituted on the nucleus by halogen or alkyl, C₁-C₈-alkyl methacrylate, C₁-C₈-alkyl acrylate or mixtures of these compounds and
- 5 to 50 parts by wt. acrylonitrile, methacrylonitrile, C₁-C₈-alkyl methacrylate, C₁-C₈-alkyl acrylate, maleic anhydride, C₁-C₄-alkyl or phenyl-N-substituted maleimide or mixtures of these compounds or 5 to 95 parts by weight of a polymer having a glass transition temperature below -10°C.
8. [Moulding compositions according to any one of claims 1 to 7,] The composition of Claim 1 which further comprise at least one additive selected from the group consisting of stabilizers, pigments, mould release agents, flow auxiliaries [and/or] and antistatics.
9. [Moulding compositions according to any one of claims 1 to 8,] The composition of Claim 1 which further comprise at least one additive selected from the group consisting of fillers [and], reinforcing materials and inorganic compounds.
- Cancel Claims 10 and 11

Please add the following:

- 12. A method of using the molding composition of Claim 1 comprising producing a molded article.
- 13. A molded article prepared by the method of Claim 12. --